


AMISEAL PSO

APPLY WITH



Airless
spraygun

**Peelable temporary protective coating for use on a wide range of surfaces such as walls and tilefloors.
For inside use only. Remove as plastic film when protection is no longer needed.**



DESCRIPTION

AMISEAL PSO is a natural polymers based liquid, which is applied by preference with an airless paintspray machine, but can also be applied with roller or paintbrush and dries to a flexible and peelable temporary protection film for use on different types of porous and non-porous substrates such as painted walls, concrete surfaces and bricks. This product is mainly used by companies removing asbestos in buildings. AMISEAL PSO is fit for use inside and does not contain solvents.

AMISEAL PSO is easily removed as a plastic film within 6 months after application and does not leave any residue.

APPLICATION

PREPARATION

- » Minimum application temperature during application and during drying: + 5°C.
- » Perform a test to verify peelability and the absence of any negative effect to the surfaces to be protected.
- » Remove loose parts, dust and standing water.
- » Mix well before use. Do not dilute with water or solvents.

APPLICATION

- » Apply AMISEAL PSO by preference with an airless paintspray device, however AMISEAL PSO can also be applied with a suitable roller or paintbrush.
- » Minimum consumption: 0,5 kg/m².
- » Protect surrounding surfaces from overspray during application.
- » Avoid contact of AMISEAL PSO with water or other products in the drying phase.
- » Cleaning of tools after application: use K-Cleaner which is an alkaline cleaning agent, and rinse thoroughly with water afterwards.

PRODUCT CHARACTERISTICS & CERTIFICATES

Chemical basis	Polymer; solventfree.
Density	+/- 1 kg/litre
Colour	Wet state: pink; after drying: typical latex colour/colourless
Odour	Neutral; slightly ammoniac
Minimum consumption	0,5 kg/m ²
Elongation (EN 12311)	800%
Dart Drop Test (ASTM D 1709)	Pass; film is not broken after projectile drop: height: 1,50 meter; diameter 50mm.
Drying time	1 to 4 hours (standard conditions)

AMISEAL PSO

APPLY WITH



Airless
spraygun

PACKAGING & STORAGE

- » Pail of 20kg – Pallet: 32 pails of 20 kg
- » Storage: 5 – 20 °C; store out of direct sunlight; Conservation: 6 months from date of production in unopened and original packaging;

SAFETY

Consult safety data sheet prior to starting the application.

DATUM OPMAAK VAN DEZE VERSIE: 18/02/2019

De algemene verkoopvoorwaarden zijn van toepassing. Dit document heeft geen enkele contractuele waarde. Deze fiche annuleert en vervangt de vorige uitgave. De gegevens op deze fiche hebben tot doel u in te lichten en raad te geven, ze zijn gebaseerd op proeven uitgevoerd met oog op objectiviteit. Wijzigingen aan deze fiche t.g.v. de technische evolutie kunnen op ieder tijdstip aangebracht worden. Gelieve u te vergewissen van de geldigheid van de fiche in uw bezit. De bovenstaande informatie is gebaseerd op onze huidige kennis. HEVADEX bvba is niet verantwoordelijk voor het gebruik van de producten indien die niet overeenstemmen met de aanbevelingen en gebruiksaanwijzingen. De aanbevelingen en gebruiksaanwijzingen zoals hierboven beschreven zijn slechts indicatief en houden geen absolute regels in aangezien bepaalde elementen aan onze controle kunnen ontsnappen. Gelieve HEVADEX bvba te raadplegen. Zij zullen u adviseren over uw specifieke toepassing.